



prime tac

200 Series

Filament 220 Industrial Grade Fiberglass Reinforced Filament Tape

Our Primetac brand 220 tape is a premium high strength filament tape built for light duty unitizing, bundling, strapping and reinforcing.



BUILT FOR BUNDLING



**IDEAL FOR
OVERSTUFFED BOXES**



QUICK TACK



**SUPERIOR PACKAGE
REINFORCEMENT**



**BUILT FOR
TEXTURED SURFACES**

BUILT FOR



Appliance



Packaging



Construction



Bundling/Palletizing



Industrial Packaging



Carton Sealing

SPECIFICATIONS

ADHESIVE
Hotmelt

BACKING
BOPP

REINFORCEMENT
Fiberglass

TOTAL THICKNESS
4.3 mil | 109 microns

TENSILE STRENGTH
112lbs / inch

FEATURES

- ✓ Clear construction allows graphics and printing to be seen through the tape
- ✓ Highly resistant to abrasion, moisture, solvent, cracking and splitting
- ✓ Impact and shock resistant
- ✓ High holding power for a wide variety of use cases
- ✓ RoHS Compliant

OTHER PHYSICAL PROPERTIES

Property	Peel Adhesion 90°	Holding Power	Elongation % at Break	Service Temp.
Standard	79 oz / in	≥36 h	3-5%	23°F - 158°F
Metric	22 N / 25mm	≥36 h	3-5%	-5°C - 70°C

CONSTRUCTION

220 backed with BOPP film and reinforced with glass fiber. Reinforced and economic mono-directional filament tape.

STORAGE AND USAGE CONDITION

Primetac tapes ideally should be stored in its original packaging in a cool, dry area away from direct sunlight exposure and from freezing. Storage temperature should be as close as possible to room temperature. Surfaces to which tape is applied should be clean, dry and free of dust, grease, oil or other contaminants. Shelf life 12 months from date of Manufacture.

**Available Sizes
And Colors**

Stock Lengths



55m

Stock Widths



9mm



12mm



18mm



24mm



48mm



72mm

We customize! Contact a representative for special sizes.

Colors

CLEAR

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The physical and performance characteristics shown are averages obtained from tests recommended by PSTC procedures in our laboratory and the user must by test or otherwise determine suitability for his purpose. There is no warranty of fitness for a particular purpose. Primetac does not take responsibility for the defective material if not stored and used in accordance with the conditions listed above. This specification sheet might change due to the continuous improvement for better quality product.