



prime tac

800 Series

805 5.5 Mil Medium Duty Reinforced Water-Activated Tape

Our water-activated reinforced kraft paper tape is a great way to get an eco-friendly, recyclable alternative to pressure sensitive adhesive tape without sacrificing carton sealing effectiveness.



BUILT FOR BOXES



ALL-WEATHER



BOND STRENGTHENS WITH TIME



PILFER-PROOF



ECO-FRIENDLY

BUILT FOR



Appliance



Food & Beverage



Packaging



Transportation



Fulfillment



Industrial Packaging



Carton Sealing

SPECIFICATIONS

ADHESIVE
Starch

BACKING
25lb Kraft Paper (Top & Btm)

Caliper
5.5 mils | 0.14 mm

Tensile Strength
MD: 65 lbs / inch
CD: 20 lbs / inch

Reinforcement
MD: 70mm 110 (1-1-1-1-1-1)
CD: 25.4mm 150 (1-1-1)

FEATURES

- ✓ Built for recycled corrugated and non-unitized loads
- ✓ Superb tensile strength
- ✓ Works best for light weight to average cartons (<31lbs/14kg)
- ✓ Eco-friendly, pollution-free material and adhesive
- ✓ Get peace of mind with pilfer-proof, tamper evident tape
- ✓ Superior durability to keep tape intact

OTHER PHYSICAL PROPERTIES

Property	Tensile Strength (MD) ASTM D-3759	Tensile Strength (CD) ASTM D-3759	Reinforcement (MD)	Reinforcement (CD)
Standard	61 lbs / in	22 lbs / in	70 mm 110 (1-1-1-1-1-1) Fiberglass	25.4 mm 150 (1-1-1) Fiberglass Diamond Pattern
Metric	270 N / 25 mm	100 N / 25 mm	70 mm 110 (1-1-1-1-1-1) Fiberglass	25.4 mm 150 (1-1-1) Fiberglass Diamond Pattern

CONSTRUCTION

Water-activated, fiberglass-reinforced kraft paper tape with starch adhesive. 5.5 mil caliper.

STORAGE AND USAGE CONDITION

Primetac tapes ideally should be stored in its original packaging in a cool, dry area away from direct sunlight exposure and from freezing. Storage temperature should be as close as possible to room temperature. Surfaces to which tape is applied should be clean, dry and free of dust, grease, oil or other contaminants. Shelf life 12 months from date of Manufacture.

Available Sizes And Colors

Stock Lengths



Stock Widths



Colors

NATURAL KRAFT

WHITE-WHITE

We customize! Contact a representative for special sizes.

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The physical and performance characteristics shown are averages obtained from tests recommended by PSTC procedures in our laboratory and the user must by test or otherwise determine suitability for his purpose. There is no warranty of fitness for a particular purpose. Primetac does not take responsibility for the defective material if not stored and used in accordance with the conditions listed above. This specification sheet might change due to the continuous improvement for better quality product.